

Series 2400 Reflecta-Cal Film

Series 2400: Non-Perforated - Series 2450: Perforated

APPLICATIONS & FEATURES

- Superior flexibility.
- Lay-flat liner.
- 7 year durability flat surfaces.
- 5 year durability irregular surfaces.
- Excellent initial tack and ultimate adhesion.
- Meets: DOT FP-85, Section 718 Federal Spec. L-S-300C ASTM-D 4956-89
- Recommended with dry application methods only.

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	80% to 90%	
THICKNESS	Micrometer, Federal Bench Type	5-mil (130 micron)	
TENSILE STRENGTH	Tensile Tester 2-in (51 mm) jaw seperation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 5.75 lb/in width	≥ 1.0 kg/cm width
ELONGATION	Instron Tensile Tester as above	≥75% • Black ≥ 40%	
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	Immersed for 100 hours at 68°F (21°C)	40°F to 100°F	5°C to 38°C
		60°F to 90°F optimum	15°C to 32°C optimum
SERVICE TEMPERATURE RANGE	Films applied to etched aluminum panels 24 hours prior to testing	-65°F to 160°F	-54°C to 71°C
HUMIDITY RESISTANCE	1. LS-300 method 4.4.10 2. ASTM-D4956-89	No appreciable effect	
FUNGUS RESISTANCE	1. LS-300 method 4.412 2. ASTM-D4956-89	No appreciable effect	
GASOLINE RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing LS-300 method 4.4.6	No appreciable effect	
PEEL ADHESION	PSTC-1, 15 min RT, 70°F (21°C)	≥ 4.4 lbs/in	≥ 0.78 kg/cm
LINER RELEASE	TLMI, 300 in/min (760 cm/min)	80 g/2 in	15 g/cm

^{*}Standard Terms & Conditions Apply

USA: a 200 Boysenberry Lane, Placentia, CA 92870, USA

EUROPE: a North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

UK: a P6 Parklands, Heywood Distribution Park, Heywood, Lancashire OL102TT, UK

INDIA: a 4F1 Court Chambers 35, New Marines Lines, Mumbai 400 020, India

f +31 0 70 355 7721

TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

USA: a 200 Boysenberry Lane, Placentia, CA 92870, USA

EUROPE: a North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

+44 0 161 884 0592

April 2014

arlon.com