



# Series 5590 Dual Color Film

## Series 5590: Perforated

### APPLICATIONS & FEATURES

- Superior release and weedability.
- Excellent initial tack and ultimate adhesion.
- Ideal for internally illuminated signage requiring maximum visibility during day and night viewing.
- Standard Product: white (120), black (122).
- Custom Colors: available upon request.
- 5 Year outdoor durability.

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	5% to 10%	
<b>THICKNESS</b>	Micrometer, Federal Bench Type	4-mil (100 micron)	
<b>TENSILE STRENGTH</b>	Tensile Tester 2-in (51mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s)	≥ 25 lb/in width	≥ 4.46 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	≤ 100%	
<b>SHELF LIFE</b>	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment	
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate	60°F to 90°F optimum	15°C to 32°C optimum
<b>SERVICE TEMPERATURE RANGE</b>	Film applied to etched aluminum panels 24 hours prior to testing	-40°F to 200°F	-40°C to 93° C
<b>HUMIDITY RESISTANCE</b>	Film applied to etched aluminum panels 24 hours prior to testing; 100% relative humidity at 100°F (38°C) for 500 hours	No appreciable effect	
<b>GASOLINE RESISTANCE</b>	Film applied to etched aluminum panels 24 hours prior to testing; 100% relative humidity at 100°F (38°C) for 500 hours	No appreciable effect	
<b>DIMENSIONAL STABILITY</b>	158°F (70°C), 48 hours	0.025 in	0.635 mm
<b>PEEL ADHESION</b>	PSTC-1, 15 min, RT 70°F (21°C)	≥ 5 lb/in	≥ 0.89 kg/cm
<b>LINER RELEASE</b>	TLMI 300 in/min (762 cm/min)	20 g/2 in	4 g/cm

\*Standard Terms & Conditions Apply

## ADHESIVE

This 4-mil (100 micron) dual color film is coated with acrylic pressure-sensitive adhesive which facilitates applications over a wide range of temperatures. Initial adhesion, ultimate adhesion and shrinkage properties have been balanced to create a product that is easy to apply, and performs to user expectations. Optimum application temperatures are between 60°F and 90°F (15°C and 30°C), but may be extended by special preparation i.e., heat gun at below 40°F (5°C) and “wet” application at above 90°F (30°C). Addition of heat during removal will make the process much cleaner and faster. Where possible allow the surface to reach 80°F/27°C or more before removing the film. Where ambient temperature is not that high use either a very “soft” flame type torch or heat gun to bring the temperature up. Arlon recommends getting the film and under laying adhesive above 100°F/38°C.

## DURABILITY

Five (5) years, unprinted. Durability will be affected by any printing or clear coating, as well as actual exposure conditions and sign face maintenance.

## USAGE AND APPLICATION INFORMATION

The properties of this application are best demonstrated when the dual color film is applied over clear acrylic or polycarbonate and a diffuser is installed as a second surface layer to the substrate. The diffuser film will hide light box components while offering good light dispersion.

For best results on large, continuous-color signs, be sure to utilize material from identical rolls on the same sign face to assure perfect color reflection and transmission across the sign face. This film is directionally sensitive; therefore, nesting characters is not recommended.

Sheets should be continuous rather than spliced. Butting splices or overlaps will create an inconsistent appearance at the joined area.

When installing large graphics on glass, Plexiglas® or acrylic sign faces, it is useful to follow “wet” application techniques. This will reduce trapped air problems and aid in repositionability for proper registration. Care should be taken to thoroughly remove entrapped water through high squeegee pressure.

Series 5590 is not compatible with standard paint systems. For print recommendations please contact your regional sales manager.

## NOTICE TO PURCHASER

Information is based on tests believed to be reliable, but neither accuracy nor completeness is guaranteed. Seller's and manufacturer's only obligation shall be to replace such quantity of the film proven to be defective. Neither the seller nor the manufacturer shall be liable for any injury, loss or damage, direct or indirect, arising from the use or inability to use this product.

## TERMS AND CONDITIONS

The customer assumes responsibility in determining product suitability for his intended end use. Seller's and manufacturer's only obligation shall be to replace product proven to be defective. Standard terms and conditions apply.

April 2014

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA  
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands  
UK:  P6 Parklands, Heywood Distribution Park, Heywood, Lancashire OL102TT, UK  
INDIA:  4F1 Court Chambers 35, New Marines Lines, Mumbai 400 020, India

 800 232 7161 / 714 540 2811  800 329 2756  
 +31 0 70 354 4311  +31 0 70 355 7721  
 +44 0 161 884 0592  +31 0 70 355 7721  
 +91 99 6755 3895

arlon.com